



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: C501
SUPPORT: 2 MIL PET
SUBSTRATE: PP
CERT NO.: 230109 - 1109

GMW 16443-TYPE-II-EXTERIOR-CYCLE-C

OEM Rev Date: Aug 18

Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam
Type II - An adhesive backed foam composite that is retained by the adhesive for the life of the vehicle

Tested in accordance with JDC protocols and provided as product information only. Actual product and application substrates would need to be tested for OEM certification.

Passing Type II Meets and Exceeds 3.5.1 Type I Exposure Requirements

TAPE REQUIREMENTS:

3.5.2 TYPE-II Exposure

SECTION 3.3.3 Edge Adhesion

3.5.3, Initial, As Received - 24 hrs @ RT

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

- 17 hrs @ -30°C
72 hrs @ 70°C
24 hrs @ 38°C / 100% RH
7 hrs @ -30°C
24 hrs @ 38°C / 100% RH
7 hrs @ 70°C
24 hrs @ 38°C / 100% RH

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

SECTION 3.4 Peel Adhesion

ISO 8510-2

3.5.3, Initial, As Received - 24 hrs @ RT

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

- 17 hrs @ -30°C
72 hrs @ 70°C
24 hrs @ 38°C / 100% RH
7 hrs @ -30°C
24 hrs @ 38°C / 100% RH
7 hrs @ 70°C

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

SECTION 3.5.8 Cold Shock

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

SECTION: 3.7.1 Release Liner

3.7.2, Liner Removal @ RT

CERTIFIED BY:

Signature of Dave Nichols Jr.
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Appendix A Table A2

PRODUCT: C501
 SUPPORT: 2 MIL PET
 SUBSTRATE: PP
 CERT NO.: 230109 - 1109

Table A2: GMW16443 Type II Applications Test Data Form

Section	Test	Standard	Requirements	Sample	Visual Edge Adhesion	Peel N/m	Failure Mode
3.5.3	Initial, As Received - 24 hrs @ RT	ISO 8510-2	Minimum of 525 N/m and Cohesive Failure of One or Both of the Adherends	1	Stable, No Lifting or Removal	1271.4	AF-P
				2	Stable, No Lifting or Removal	1294.2	AF-P
				3	Stable, No Lifting or Removal	1274.9	AF-P
3.5.4	Heat Aged 168 hrs @ 80°C per ISO 188			1	Stable, No Lifting or Removal	1080.5	AF-P
				2	Stable, No Lifting or Removal	1059.5	AF-P
				3	Stable, No Lifting or Removal	1155.8	AF-P
3.5.5	Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A			1	Stable, No Lifting or Removal	1649.7	CF
				2	Stable, No Lifting or Removal	1544.6	CF
				3	Stable, No Lifting or Removal	1721.5	CF
3.5.6	Cycle Exposure, GMW 14124, 2x Cycle C			1	Stable, No Lifting or Removal	1199.6	AF-P
				2	Stable, No Lifting or Removal	1325.7	AF-P
				3	Stable, No Lifting or Removal	1287.2	AF-P
				1			
				2			
				3			
3.5.8	Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C	1	Stable, No Lifting or Removal	1397.5	CF		
		2	Stable, No Lifting or Removal	1478.1	CF		
		3	Stable, No Lifting or Removal	1413.3	CF		

Section	Test	Standard	Requirements	Sample	Result
3.6	Tape Wet Out, GMW15851	GMW 15851 is restricted and we cannot purchase	85% Tape Wet Out	1	Not Tested
				2	Not Tested
				3	Not Tested
3.7.1	Release Liner Contact	To Be Determined @ Tier	No Lift Prior To Vehicle Install	1	TBD
				2	TBD
				3	TBD
3.7.2	Liner Removal	ISO 8510-2	Less Than or Equal To 65 N/m	1	5.3
				2	8.8
				3	7.0