

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com URL: stus.averydennison.com

PP

SUBSTRATE:

STD CERT NO.: 221215 - 1517

GMW 16875 TYPE IA-CYCLE-D

OEM Rev Date: Oct 18

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

TEST REPORT

FT 1149X

0.5 MM FELT

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV

TESTING LABORATORY

Initial

PRODUCT:

SUPPORT:

TAPE REQUIREMENTS

Not Applicable

SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	Results 23.9	<u>Status</u> Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 350 N/m	<u>Results</u> 1473.8	Status Pass
Humidity, 24 hrs @ 38°C / 959	% RH	350 N/m	1556.6	Pass
Aged, 168 hrs @ 70°C		350 N/m	1637.2	Pass
GMW 14124 CYCLE D	24 hrs @ 38°C / 100% RH	350 N/m	1662.3	Pass

24 hrs @ 38°C / 100% RH

4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C

SECTION: Shear Strength, MD	ASTM D1000	Specification	Results	<u>Status</u>
4 hrs @ -18°C		7500 N/m	5283.9	т Pass

3500 N/m 2310.2 24 hrs @ 60°C т Pass

SECTION: Taber Abrasion*	GMW3208	Specification	Results	<u>Status</u>
500 Cycles CS-10,1 kg Load		No Wear Thru to Fabric Backing	Worn But Not Thru	Pass

SECTION: Flammability	GMW3232	<u>Specification</u>	Results	<u>Status</u>
Initial, Component		100 mm / min	< B 25	Pass

SECTION: Xenon Weatherometer*	GMW14162	Specification	Results	<u>Status</u>

No Degradation, Stiffening,

Bleaching or Objectionable Color							
SECTION: Odor*	GMW3205	<u>Specification</u>	Results	Status			

Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water 6 Min Rating 8 Noticeable, Trace **Pass** Dry Condition, Coding B - 24 hrs @ 70°C 7 Clearly Noticeable, But Not Objectionable **Pass** High Temp Condition - 24 hrs @ 105°C 7 Clearly Noticeable, But Not Objectionable **Pass**

Specification SECTION: VOC* GMW15634 Results **Status** Per GMW 16853 6 mg Not Tested NA

SECTION: Gravimetric Fogging GMW3235 Method B **Specification** Results **Status**

18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant 1.26 < 2 mg **Pass**

CERTIFIED BY:

1-1-24 ISSUE DATE:

Dave Nichols Jr, Automotive Lab Technician

Not Applicable

NA