

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT A902 SUPPORT: FLOCK SUBSTRATE: ABS

STD CERT NO.: 230926 - 0715

GMW 16875 TYPE IA-CYCLE-D

OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

Considienties

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV

ACCREDITED

TESTING LABORATORY

Pass

Dogulto

Initia

100 0540 0



Initial RT	ISO 8510-2	900 N/m	39.3	Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 350 N/m	<u>Results</u> 721.8	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		350 N/m	957.3	Pass
Aged, 168 hrs @ 70°C		350 N/m	999.8	Pass
GMW 14124 CYCLE D 24 hrs @ 3	8°C / 100% RH	350 N/m	952.3	Pass

4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C

4 hrs @ -30C 100 hrs @ 70°C

SECTION: Shear Strength, MD	ASTM D1000	<u>Specification</u>	Results	Status
4 hrs @ -18°C		7500 N/m	10861.0	т Pass

24 hrs @ 60°C 3500 N/m 5821.3

SECTION: Taber Abrasion*	GMW3208	<u>Specification</u>	Results	<u>Status</u>
500 Cycles CS-10,1 kg Load		No Wear Thru to Fabric Backing	Worn But Not Thru	Pass

SECTION: Flammability	GMW3232	Specification	Results	<u>Status</u>
Initial, Component		100 mm / min	< B 25	Pass

SECTION: Xenon Weatherometer*	GMW14162	Specification	Results	Status
Not Applicable		No Degradation, Stiffening,	Not Applicable	NA
		Bleaching or Objectionable Color		

SECTION: Odor*	GMW3205	<u>Specification</u>	Results	<u>Status</u>
Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water		6 Min Rating	Not Tested	NT
Dry Condition, Coding B - 24 hrs (n 70°C		Not Tested	NT

Dry Condition, Coding B - 24 hrs @ 70°C

High Temp Condition - 24 hrs @ 105°C

Not Tested

NT

Not Tested

NT

SECTION: VOC* GMW15634 Specification Results Not Tested NA

SECTION: Gravimetric Fogging GMW3235 Method B Specification Results 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant 2 mg 1.2 Pass

CERTIFIED BY:



ISSUE DATE: <u>1-1-24</u>

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.