			TEST REPORT		
250 Chester Street Painesville, Ohio 44077 Phone: 866-GO-AVERY (866 Fax: 888-358-4469 email: psa.tape@averydenn URL: tapes.averydennisor	nison.com	OEM Rev Date Performance R	YPE IA-CYCLE-D e: Jan 13 Requirements of Anti-Squeak, Itch,	Rattle Fiber Tape ated with a permanent acrylic PSA not exposed to	
TAPE REQUIREMENTS: SECTION: Liner Removal Initial RT		ISO 8510-2	Specification 900 N / m	Results 24.5	<u>Status</u> Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT		ISO 8510-2	Specification 350 N / m	<u>Results</u> 915.8	<u>Status</u> Pass
Humidity, 24 hrs @ 38°C / 95%	RH		350 N / m	1435.8	Pass
Aged, 168 hrs @ 70°C			350 N/m	1361.7	Pass
1	24 hrs @ 38°C / 4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C	′ 100% RH	350 N / m	1268.3	Pass
SECTION: Shear Strength, N 4 hrs @ -18°C	1D	ASTM D1000	Specification 7500 N / m	<u>Results</u> 14287.0	<u>Status</u> ⊤ Pass
24 hrs @ 60°C			3500 N/m	9512.6	Pass
SECTION: Taber Abrasion* 500 Cycles CS-10,1 kg Load		GMW3208	Specification No Wear Thru to Fabric Backing	<u>Results</u> Worn But Not Thru	<u>Status</u> Pass
SECTION: Flammability Initial, Component		GMW3232	Specification 100 mm / min	Results < B 25	<u>Status</u> Pass
SECTION: Xenon Weatheron Not Applicable	neter*	GMW14162	<u>Specification</u> No Degradation, Stiffening, Bleaching or Objectionable Color	Results Not Applicable	<u>Status</u> NA
SECTION: Odor* Wet Condition, Coding A - 24 h Dry Condition, Coding B - 24 hr High Temp Condition - 24 hrs @	rs @ 70°C	GMW3205 zed Water	Specification 6 Min Rating	Results 8 Noticeable, Trace 8 Noticeable, Trace 7 Clearly Noticeable, But Not Objectionable	<u>Status</u> Pass Pass Pass
SECTION: VOC* Per GMW 16853		GMW15634	Specification 6 mg	<u>Results</u> Not Tested	<u>Status</u> Not Tested
SECTION: Gravimetric Fogg 18 hrs @ 100°C, 21°C Cooling	-	MW3235 Method B <mark>ant</mark>	Specification 2 mg	<u>Results</u> 0.00042	<u>Status</u> Pass
CERTIFIED BY:	Is Jr, Automotive Lab Te	achnician		ISSUE DATE: <u>1-1-24</u>	

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date:

3-30-2022 Page 1 of 1