



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

### TEST REPORT

PRODUCT: FT A912  
SUPPORT: FLOCK  
SUBSTRATE: PP  
STD CERT NO.: 230913 - 0849



**GMW 16875 TYPE IA-CYCLE-D**  
OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape  
Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV Initial

**TAPE REQUIREMENTS:**

SECTION:	Standard	Specification	Results	Status
SECTION: <b>Liner Removal</b> Initial RT	ISO 8510-2	<b>900 N / m</b>	18.2	<b>Pass</b>
SECTION: <b>Peel Adhesion</b> Aged, 72 hrs @ RT	ISO 8510-2	<b>350 N / m</b>	515.8	<b>Pass</b>
Humidity, 24 hrs @ 38°C / 95% RH		<b>350 N / m</b>	553.7	<b>Pass</b>
Aged, 168 hrs @ 70°C		<b>350 N / m</b>	530.6	<b>Pass</b>
GMW 14124 CYCLE D		<b>350 N / m</b>	524.4	<b>Pass</b>
24 hrs @ 38°C / 100% RH				
4 hrs @ 85°C				
3 hrs @ RT				
17 hrs @ 85°C				
168 hrs @ 70°C				
4 hrs @ -30C				
100 hrs @ 70°C				
SECTION: <b>Shear Strength, MD</b> 4 hrs @ -18°C	ASTM D1000	<b>7500 N / m</b>	10824.1	<b>Pass</b>
24 hrs @ 60°C		<b>3500 N / m</b>	6487.5	<b>Pass</b>
SECTION: <b>Taber Abrasion*</b> 500 Cycles CS-10,1 kg Load	GMW3208	<b>No Wear Thru to Fabric Backing</b>	Worn But Not Thru	<b>Pass</b>
SECTION: <b>Flammability</b> Initial, Component	GMW3232	<b>100 mm / min</b>	SE/NBR	<b>Pass</b>
SECTION: <b>Xenon Weatherometer*</b> Not Applicable	GMW14162	<b>No Degradation, Stiffening, Bleaching or Objectionable Color</b>	Not Applicable	<b>NA</b>
SECTION: <b>Odor*</b> Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water Dry Condition, Coding B - 24 hrs @ 70°C High Temp Condition - 24 hrs @ 105°C	GMW3205	<b>6 Min Rating</b>	Not Tested Not Tested Not Tested	<b>NT</b> <b>NT</b> <b>NT</b>
SECTION: <b>VOC*</b> Per GMW 16853	GMW15634	<b>6 mg</b>	Not Tested	<b>NA</b>
SECTION: <b>Gravimetric Fogging</b> 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant	GMW3235 Method B	<b>2 mg</b>	1.8	<b>Pass</b>

CERTIFIED BY:



Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.