

250 Chester Street

Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: A915-80
SUPPORT: FLOCK
SUBSTRATE: ABS

STD CERT NO.: 221215 - 1506

GMW 16875 TYPE IA-CYCLE-D

OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV

ACCREDITED

TESTING LABORATORY

Pass

Initia



SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	<u>Results</u> 78.8	Status Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 350 N/m	<u>Results</u> 741.3	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		350 N/m	1497.7	Pass
Aged, 168 hrs @ 70°C		350 N/m	1335.4	Pass
GMW 14124 CYCLE D 24 hrs @ 4 hrs @		350 N/m	1206.4	Pass

4 hrs @ 85°C
3 hrs @ RT
17 hrs @ 85°C
168 hrs @ 70°C
4 hrs @ -30C
100 hrs @ 70°C

SECTION: Shear Strength, MD	ASTM D1000	<u>Specification</u>	<u>Results</u>	Status
4 hrs @ -18°C		7500 N/m	13907.0	т Pass

24 hrs @ 60°C 3500 N/m 9684.2

SECTION: Taber Abrasion*	GMW3208	<u>Specification</u>	Results	<u>Status</u>
500 Cycles CS-10,1 kg Load		No Wear Thru to Fabric Backing	Worn But Not Thru	Pass

SECTION: Flammability	GMW3232	<u>Specification</u>	<u>Results</u>	Status_
Initial, Component		100 mm / min	< B 25	Pass

SECTION: Xenon Weatherometer* GMW14162 Specification Results Status
Not Applicable No Degradation, Stiffening, Not Applicable
Bleaching or Objectionable Color

SECTION: Odor*	GMW3205	Specification	<u>Results</u>	<u>Status</u>
Wet Condition, Coding A - 24 hrs @	70°C, Deionized Water	6 Min Rating	9 Just Noticeable	Pass
Dry Condition, Coding B - 24 hrs @ 7	70°C		9 Just Noticeable	Pass
High Temp Condition - 24 hrs @ 105	°C		8 Noticeable, Trace	Pass

SECTION: VOC* GMW15634 Specification Results Status
Per GMW 16853 For GMW 16854 Not Tested Not Tested

SECTION: Gravimetric Fogging GMW3235 Method B Specification Results Status

18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant 2 mg 0.00013 Pass

CERTIFIED BY:

ISSUE DATE: <u>1-1-24</u>

Dave Nichols Jr, Automotive Lab Technician

 $Materials \ tested \ to \ OEM \ requirements \ @ \ 72^{\circ}F \ +/- \ 2^{\circ}F \ and \ 50\% \ RH \ +/- \ 5\%. \ Test \ uncertainty \ and \ minor \ exclusions \ are \ available \ online \ or \ upon \ request.$

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.