

250 Chester Street

Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **BNW 2028LV** SUPPORT: **FLOCK**

PP SUBSTRATE:

STD CERT NO.: 221215 - 1527

GMW 16875 TYPE IA-CYCLE-D

OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV

ACCREDITED

TESTING LABORATORY

Pass



24 hrs @ 60°C

SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	Results 1.4	Status Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 350 N/m	<u>Results</u> 484.4	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		350 N/m	466.3	Pass
Aged, 168 hrs @ 70°C		350 N/m	383.5	Pass
GMW 14124 CYCLE D 24 hrs (© 38°C / 100% RH	350 N/m	359.0	Pass

4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C

100 hrs @ 70°C

SECTION: Shear Strength, MD 4 hrs @ -18°C	ASTM D1000	Specification 7500 N / m	<u>Results</u> 5785.3	Status T Pass
24 hrs @ 60°C		3500 N/m	6590.8	Pass

SECTION: Taber Abrasion*	GMW3208	Specification	Results	Status
500 Cycles CS-10,1 kg Load		No Wear Thru to Fabric Backing	Worn But Not Thru	Pass

SECTION: Flammability	GMW3232	Specification	Results	Status
Initial, Component		100 mm / min	< B 25	Pass

SECTION: Xenon Weatherometer*	GMW14162	Specification	Results	Status
Not Applicable		No Degradation, Stiffening,	Not Applicable	NA
		Bleaching or Objectionable Color		

SECTION: Odor* Specification Results GMW3205 Status Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water 6 Min Rating 8 Noticeable, Trace Pass Dry Condition, Coding B - 24 hrs @ 70°C 9 Just Noticeable **Pass**

High Temp Condition - 24 hrs @ 105°C 8 Noticeable, Trace **Pass**

Specification SECTION: VOC* GMW15634 Results **Status** Per GMW 16853 6 mg Not Tested **Not Tested**

SECTION: Gravimetric Fogging GMW3235 Method B Specification Results Status 0.00080 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant 2 mg **Pass**

CERTIFIED BY:

1-1-24 ISSUE DATE:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.