

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com URL: tapes.averydennison.com



## **GMW 16875 TYPE IA-CYCLE-D**

ABS

OEM Rev Date: Oct 18

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV

PRODUCT:

SUPPORT:

SUBSTRATE:

STD CERT NO.:

TAPE REQUIREMENTS: SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	Results 13.9	Status Pass
SECTION: <b>Peel Adhesion</b> Aged, 72 hrs @ RT	ISO 8510-2	Specification 350 N/m	Results 600.0	Status T Pass
Humidity, 24 hrs @ 38°C / 95% RH		350 N/m	1235.3	т Pass
Aged, 168 hrs @ 70°C		350 N/m	1020.0	т Pass
GMW 14124 CYCLE D  24 hrs @ : 4 hrs @ : 3 hrs @ : 17 hrs @ : 168 hrs @ : 4 hrs @ - 100 hrs @ :	RT 85°C 70°C 30C	350 N/m	815.7	T Pass
SECTION: Shear Strength, MD	ASTM D1000	Specification 7500 N/m	Results	Status

SECTION: Odor*	GMW/3205	Specification	Results	Status
SECTION: Xenon Weatherometer* Not Applicable	GMW14162	Specification  No Degradation, Stiffening,  Bleaching or Objectionable Color	Results Not Applicable	Status NA
SECTION: Flammability Initial, Component	GMW3232	Specification 100 mm/min	Results < B 25	Status Pass
SECTION: <b>Taber Abrasion*</b> 500 Cycles CS-10,1 kg Load	GMW3208	Specification No Wear Thru to Fabric Backing	Results Not Tested	<u>Status</u> Not Tested
24 hrs @ 60°C		3500 N/m	3261.5	т Pass
SECTION: Shear Strength, MD 4 hrs @ -18°C	ASTM D1000	Specification 7500 N/m	<u>Results</u> 4661.2	Status T Pass

SECTION: Odor*	GMW3205	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Wet Condition, Coding A - 24 hrs @	70°C, Deionized Water	6 Min Rating	Not Tested	Not Tested
Dry Condition, Coding B - 24 hrs @ 7	70°C		Not Tested	Not Tested
High Temp Condition - 24 hrs @ 105	°C		Not Tested	Not Tested

SECTION: VOC*	GMW15634	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Per GMW 16853		6 mg	Not Tested	NA

**SECTION: Gravimetric Fogging** GMW3235 Method B **Specification** Results **Status** 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant 1.0 < 2 mg **Pass** 

CERTIFIED BY:

1-1-24 ISSUE DATE:

David Nichols II, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.