

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com URI ·

tapes.averydennison.com

## **TEST REPORT**

PRODUCT: **BNW 5027** SUPPORT: **FELT** SUBSTRATE:

STD CERT NO.: 240717 - 0822



ACCREDITED TESTING LABORATORY

## **GMW 16875 TYPE IA-CYCLE-D**

OEM Rev Date: Oct 18

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV

Initial

T /	D	D		$\sim$		Ю	۱л	NIT	rs:
	٩г	$\mathbf{r}$	_	w	u	п	VI	v	ı o.

SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	<u>Results</u> 13.9	Status Pass
SECTION: <b>Peel Adhesion</b> Aged, 72 hrs @ RT	ISO 8510-2	Specification 350 N/m	Results 420.6	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		350 N/m	431.6	Pass
Aged, 168 hrs @ 70°C		350 N/m	456.4	Pass
GMW 14124 CYCLE D  24 hrs @ 3 4 hrs @ 8 3 hrs @ 6 17 hrs @ 8	RT	350 N/m	543.9	Pass

168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C

SECTION: Shear Strength, MD	ASTM D1000	Specification	Results	<u>Status</u>
4 hrs @ -18°C		7500 N/m	4405.2	т Pass

3500 N/m 2965.1 24 hrs @ 60°C т Pass

SECTION: Taber Abrasion\* GMW3208 Specification Results **Status** 500 Cycles CS-10,1 kg Load No Wear Thru to Fabric Backing Not Tested **Not Tested** 

**SECTION: Flammability Specification** GMW3232 Results **Status** 100 mm/min < B 25 Initial, Component **Pass** 

**Specification** SECTION: Xenon Weatherometer\* GMW14162 Results **Status** Not Applicable No Degradation, Stiffening, Not Applicable NA

SECTION: Odor\* GMW3205 **Specification** Results **Status** Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water 6 Min Rating Not Tested **Not Tested** 

**Bleaching or Objectionable Color** 

Dry Condition, Coding B - 24 hrs @ 70°C Not Tested **Not Tested** High Temp Condition - 24 hrs @ 105°C Not Tested **Not Tested** 

SECTION: VOC\* **Specification** Results GMW15634 **Status** Per GMW 16853 6 mg Not Tested NA

**SECTION: Gravimetric Fogging** GMW3235 Method B **Specification** Results **Status** 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant 1.0 < 2 mg **Pass** 

CERTIFIED BY:

ISSUE DATE: 1-1-24

David Nichols II, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.