

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com URL:

tapes.averydennison.com

TEST REPORT

PRODUCT: **UHMW 327** SUPPORT: **POLYETHYLENE**

SUBSTRATE: **ABS**

STD CERT NO.: 240717 - 0747

GMW 16875 TYPE IA-CYCLE-D

OEM Rev Date: Oct 18

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV

ACCREDITED

TESTING LABORATORY

Initial

TAPE REQUI	REMENTS:
------------	----------

SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	<u>Results</u> 5.8	Status Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 350 N/m	<u>Results</u> 930.1	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		350 N/m	1108.4	Pass
Aged, 168 hrs @ 70°C		350 N/m	1522.8	Pass
GMW 14124 CYCLE D 24 hrs @ 3 4 hrs @ 17 hrs @ 17 hrs @ 1	RT	350 N/m	1411.1	Pass

17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C

SECTION: Shear Strength, MD	ASTM D1000	Specification	<u>Results</u>	<u>Status</u>
4 hrs @ -18°C		7500 N/m	3141.1	Fail

24 hrs @ 60°C 3500 N/m 3101.0 Fail

SECTION: Taber Abrasion*	GMW3208	<u>Specification</u>	<u>Results</u>	<u>Status</u>
500 Cycles CS-10,1 kg Load		No Wear Thru to Fabric Backing	Not Tested	Not Tested

SECTION: Flammability	GMW3232	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Initial, Component		100 mm / min	< B 50	Pass

SECTION: Xenon Weatherometer*	GMW14162	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Not Applicable		No Degradation, Stiffening,	Not Applicable	NA
		Bleaching or Objectionable Color		

SECTION: Odor*	GMW3205	Specification	<u>Results</u>	<u>Status</u>
Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water		6 Min Rating	Not Tested	Not Tested
Dry Condition, Coding B - 24 hrs @ 7	0°C		Not Tested	Not Tested

Dry Condition, Coding B - 24 hrs @ 70° C High Temp Condition - 24 hrs @ 105°C Not Tested **Not Tested**

SECTION: VOC*	GMW15634	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Per GMW 16853		6 mg	Not Tested	NA

SECTION: Gravimetric Fogging GMW3235 Method B **Specification** Results **Status** 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant 0.6 < 2 mg **Pass**

CERTIFIED BY:

1-1-24 ISSUE DATE:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.