

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com URL:

tapes.averydennison.com

TEST REPORT

FT A902 PET PRODUCT:

SUPPORT: **FLOCK** PP SUBSTRATE:

230922 - 0608 STD CERT NO.:

GMW 16875 TYPE II-CYCLE-D

OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape Type II material is a nonwoven tape coated with a permanent acrylic PSA

Initial

GMW3208



TAPE R	EQUIRE	MENTS:
--------	--------	--------

SECTION: Taber Abrasion*

SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	<u>Results</u> 19.3	Status Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 280 N/m	Results 438.3	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		280 N/m	570.2	Pass
Aged, 168 hrs @ 70°C		280 N/m	524.7	Pass
GMW 14124 CYCLE D 24 hrs @ 4 hrs @ 3 hrs @ 17 hrs @ 168 hrs @ 4 hrs @	RT 85°C 70°C	280 N/m	597.7	Pass

SECTION: Shear Strength, MD	ASTM D1000	Specification	<u>Results</u>	Status
4 hrs @ -18°C		2500 N/m	7701.5	T Pass
24 hrs @ 60°C		2500 N/m	11249.6	Pass

500 Cycles CS-10,0.5 kg Load		No Wear Thru to Fabric Backing	Worn But Not Thru	Pass	
SECTION: Flammability Initial, Component	GMW3232	Specification 100 mm / min	<u>Results</u> < B 25	Status Pass	

Specification

SECTION: Xenon Weatherometer*	GMW14162	Specification Processing Specification Process	<u>Results</u>	<u>Status</u>
Not Applicable		No Degradation, Stiffening,	Not Applicable	NA
		Bleaching or Objectionable Color		

SECTION: Odor*	GMW3205	<u>Specification</u>	Results	<u>Status</u>
Wet Condition, Coding A - 24 hrs @ 70°C,	Deionized Water	6 Min Rating	Not Tested	NT
Dry Condition, Coding B - 24 hrs @ 70°C			Not Tested	NT
High Temp Condition - 24 hrs @ 105°C			Not Tested	NT

SECTION: VOC*	GMW15634	Specification	Results	<u>Status</u>
Per GMW 16853		6 mg	Not Tested	Not Tested

		_		
SECTION: Gravimetric Fogging 18 hrs @ 100°C, 21°C Cooling, 24 hr RT	GMW3235 Method B	Specification 2 mg	<u>Results</u> 1.4000	Status Pass
10 1113 @ 100 0, 21 0 0001111g, 24 111 1(1	Desideant	9	1.4000	. 400

CERTIFIED BY:



100 hrs @ 70°C

1-1-24 ISSUE DATE:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Results

Status