	AVERY DENNISON
--	-------------------

 250 Chester Street

 Painesville, Ohio 44077

 Phone:
 866-GO-AVERY (866-462-8379)

 Fax:
 888-358-4469

 email:
 psa.tape@averydennison.com

 URL:
 tapes.averydennison.com

TEST REPORT

 PRODUCT:
 BNW 5028LV

 SUPPORT:
 FELT

 SUBSTRATE:
 ABS

 STD CERT NO.:
 240717 - 0843



Not Tested

Status

Pass

Status

NA

Status

Not Tested

Not Tested

Not Tested

Status

NA

Status

Pass

GMW 16875 TYPE II-CYCLE-D OEM Rev Date: Oct 18

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape Type II material is a nonwoven tape coated with a permanent acrylic PSA Initial

TAPE REQUIREMENTS: SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	<u>Results</u> 7.6	<u>Status</u> Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 280 N / m	<u>Results</u> 1154.7	<u>Status</u> т Pass
Humidity, 24 hrs @ 38ºC / 95% RH		280 N/m	1812.9	т Pass
Aged, 168 hrs @ 70ºC		280 N/m	564.3	т Pass
	s @ 38⁰C / 100% RH s @ 85⁰C	280 N/m	849.5	т Pass

3 hrs @	RT
17 hrs @	85°C
168 hrs @	70°C
4 hrs @	-30C

GMW14162

GMW15634

100 hrs @ 70°C

SECTION: Shear Strength, MD ASTM D1000 4 hrs @ -18°C	ASTM D1000	Specification 2500 N / m	<u>Results</u> 5754.4	<u>Status</u> τ Pass
24 hrs @ 60°C		2500 N/m	4727.1	т Pass
SECTION: Taber Abrasion*	GMW3208	Specification	<u>Results</u>	<u>Status</u>

SECTION: Taber Abrasion* 500 Cycles CS-10,0.5 kg Load

SECTION: Flammability GMW3232 Initial, Component

SECTION: Xenon Weatherometer* Not Applicable

SECTION: Odor* GMW3205 Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water Dry Condition, Coding B - 24 hrs @ 70°C High Temp Condition - 24 hrs @ 105°C

SECTION: VOC* Per GMW 16853

SECTION: Gravimetric Fogging GMW3235 Method B 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

Specification No Wear Thru to Fabric Backing

> Specification 100 mm / min

Specification No Degradation, Stiffening, Bleaching or Objectionable Color

> Specification 6 Min Rating

Specification 6 mg

Specification < 2 mg

ISSUE DATE:

1-1-24

Not Tested

Results

< B 25

Results

Not Applicable

Results

Not Tested

Not Tested

Not Tested

Results

Not Tested

Results

1.5

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date: