

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: UHMW 327
SUPPORT: POLYETHYLENE

SUBSTRATE: ABS

STD CERT NO.: 240717 - 0752



GMW 16875 TYPE II-CYCLE-D

OEM Rev Date: Oct 18

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape Type II material is a nonwoven tape coated with a permanent acrylic PSA

Initial

100 hrs @ 70°C

TAPE REQUIREMENTS:

SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	Results 5.8	Status Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 280 N/m	<u>Results</u> 930.1	<u>Status</u> Pass
Humidity, 24 hrs @ 38°C / 95% RH		280 N/m	1108.4	Pass
Aged, 168 hrs @ 70°C		280 N/m	1522.8	Pass
GMW 14124 CYCLE D 24 hrs @ 38° 4 hrs @ 85° 3 hrs @ RT 17 hrs @ 85° 168 hrs @ 70° 4 hrs @ -300°	c c	280 N/m	1411.1	Pass

SECTION: Shear Strength, MD 4 hrs @ -18°C	ASTM D1000	Specification 2500 N/m	<u>Results</u> 3141.1	Status Pass
24 hrs @ 60°C		2500 N/m	3101.0	Pass
SECTION: Taber Abrasion* 500 Cycles CS-10,0.5 kg Load	GMW3208	<u>Specification</u> No Wear Thru to Fabric Backing	<u>Results</u> Not Tested	Status Not Tested
SECTION: Flammability Initial, Component	GMW3232	Specification 100 mm / min	Results < B 50	Status Pass
SECTION: Xenon Weatherometer* Not Applicable	GMW14162	Specification No Degradation, Stiffening, Bleaching or Objectionable Color	Results Not Applicable	Status NA

SECTION: Odor*	GMW3205	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Wet Condition, Coding A - 24 hrs @ 70°C, D	eionized Water	6 Min Rating	Not Tested	Not Tested
Dry Condition, Coding B - 24 hrs @ 70°C			Not Tested	Not Tested
High Temp Condition - 24 hrs @ 105°C			Not Tested	Not Tested

SECTION: VOC*	GMW15634	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Per GMW 16853		6 mg	Not Tested	NA

SECTION: Gravimetric Fogging GMW3235 Method B Specification Results Status 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant < 2 mg 0.6 Pass

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE: <u>1-1-24</u>

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.