TEST REPORT



250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

888-358-4469 Fax:

psa.tape@averydennison.com email:


URL: stus.averydennison.com PRODUCT: FT 8217 SUPPORT: 3 MM FELT SUBSTRATE: TPO

STD CERT NO.: 221216 - 0940

GMW 16875 TYPE II-CYCLE-E

Type II material is a nonwoven tape coated with a permanent acrylic PSA

TYPE II



ACCREDITED

TESTING LABORATORY

' Clearly Noticeable, But Not Objectionable

5-14-2019

Page 1 of 1

Pass

Initial

TAPE REQU	JIKEMEN 19:
SECTION: I	iner Removal

SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	Results 18.7	Status Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 280 N/m	<u>Results</u> 738.9	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		280 N/m	908.2	Pass
Aged, 168 hrs @ 70°C		280 N/m	1364.0	Pass
GMW 14124 CYCLE E		280 N/m	1421.8	Pass

72 hrs @ 70°C

24 hrs @ 38°C / 100% RH

8 hrs @ -30°C 40 hrs @ 70°C

24 hrs @ 38°C / 100% RH

8 hrs @ -30°C

SECTION: Shear Strength, MD	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
4 hrs @ -18°C		2500 N/m	9457.7	т Pass

2500 N/m 2524.4 24 hrs @ 60°C **Pass**

SECTION: Taber Abrasion*	GMW3208	<u>Specification</u>	<u>Results</u>	<u>Status</u>
500 Cycles CS-10,0.5 kg Load		No Wear Thru to Fabric Backing	Severly Worn But Not Thru	Pass

SECTION: Flammability	GMW3232	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Initial, Component		100 mm / min	25.0	Pass

SECTION: Xenon Weatherometer*	GMW14162	Specification	<u>Results</u>	<u>Status</u>
Not Applicable		No Degradation, Stiffening,	Not Applicable	NA
		Bleaching or Objectionable Color		

SECTION: Odor*	GMW3205	Specification	<u>Results</u>	<u>Status</u>
Wet Condition, Coding A - 24 hrs @ 7	70°C, Deionized Water	6 Min Rating	9 Just Noticeable	Pass
Dry Condition, Coding B - 24 hrs @ 7	0°C		8 Noticeable, Trace	Pass

SECTION: VOC*	GMW15634	Specification	<u>Results</u>	<u>Status</u>
Per GMW		6 mg	Not Tested	NA

SECTION: Gravimetric Fogging	GMW3235 Method B - HAAKE	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Initial, Component		2 mg	0.28	Pass

CERTIFIED BY:

High Temp Condition - 24 hrs @ 105°C

Dave Nichols Jr, Automotive Lab Technician

1-1-24 ISSUE DATE: