



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **stus.averydennison.com**

TEST REPORT

PRODUCT: **FT 0900X PET**
 SUPPORT: **FLOCK**
 SUBSTRATE: **FOIL**
 STD CERT NO.: **221216 - 0957**



GMW 3235 Method B
 Test Method Rev Date: Aug 16
 Fogging Characteristics of Trim Materials
 Y1 Materials with low water absorption (e.g. upholstery, fabrics, foam, artificial leather)
 T2 100°C
 Reference Spec : GMW 16875

TAPE REQUIREMENTS:

SECTION: Fogging	GMW 3235 Method B	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Product, 18 hrs @ 100°C, 21°C Cooling, 24 hr Desiccator @ RT		≤ 2 mg max	0.325	Pass

Product, 18 hrs @ 100°C, 21°C Cooling, 24 hr Desiccator @ RT		≤ 2 mg max	0.250	Pass
--	--	-------------------	-------	-------------

Product, 18 hrs @ 100°C, 21°C Cooling, 24 hr Desiccator @ RT		≤ 2 mg max	0.400	Pass
--	--	-------------------	-------	-------------

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.