



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **AFB 8340**
 SUPPORT: **2 MIL FOIL**
 SUBSTRATE: **ABS**
 CERT NO.: **221221 - 1305**



HONDA 7490Z-TK8-0000
 OEM Rev Date: Nov 09
 Adhesive For Exterior Automotive Applications
 Type II Mechanically Fastened Part

TAPE REQUIREMENTS:

SECTION:		4.4	<u>Specification</u>	<u>Min</u>	<u>Max</u>	<u>Results</u>	<u>Status</u>
1. Static Shear			200 mins	682	766	727	Pass
1-2 High Temperature, 30 min Acclimation, Test @ 80°C							

SECTION:		4.6	<u>Specification</u>	<u>Min</u>	<u>Max</u>	<u>Results</u>	<u>Status</u>
3. 90° Peel Strength			0.6 N / mm	6.9	9.4	7.76	Pass
3-2 High Temperature, 30 min Acclimation, Test @ 80°C							

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.