



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 8728**
SUPPORT: **ALUMINUM FOIL**
SUBSTRATE: **PAPER BOARD**
CERT NO.: **221221 - 1302**



HYUNDAI MS 711-12 Type A2
OEM Rev Date: Jan 03
Decorative Sheets (Pressure Sensitive Adhesive Baked Bonding Type) - Interior Trims
A2 - Ordinary tape for general use laminated on a metallic sheet such as an aluminum sheet, used in general purpose

TAPE REQUIREMENTS:

SECTION:	Specification	Results	Status
SECTION: Shear Strength			
4.4 Normal State Adhesion, 20 mins @ RT	3.0 kg / cm²	2.44 Tear	Pass
4.5 Oven Aging, 168 hrs @ 80°C	3.0 kg / cm²	4.1	Pass
4.6 Heat Cycle, 1x 3 hrs @ 80°C 1 hr @ 20°C 3 hrs @ -30°C 1 hr @ 20°C 15 hrs @ 40°C / 95% RH 1 hr @ 20°C	2.5 kg / cm²	3.6	Pass
4.15 Humidity, 168 hrs @ 40°C / 95% RH	2.5 kg / cm²	3.4	Pass
SECTION: Appearance			
4.5 Oven Aging, 168 hrs @ 80°C	No Discoloring, Peeling, Creasing, Etc.	Stable, No Discoloring, Creasing or Peeling	Pass
4.6 Heat Cycle, 1x		Stable, No Discoloring, Creasing or Peeling	Pass
4.15 Humidity, 168 hrs @ 40°C / 95% RH		Stable, No Discoloring, Creasing or Peeling	Pass
SECTION: Staining, Swelling			
4.5 Oven Aging, 168 hrs @ 80°C	No Staining or Swelling On Applicable Materials	No Staining, Lifting or Removal	Pass
4.6 Heat Cycle, 1x		No Staining, Lifting or Removal	Pass
4.15 Humidity, 168 hrs @ 40°C / 95% RH		No Staining, Lifting or Removal	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.