



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: 866-GO-AVERY (866-462-8379)  
 Fax: 888-358-4469  
 email: psa.tape@averydennison.com  
 URL: tapes.averydennison.com

**TEST REPORT**

PRODUCT: FT 8327  
 SUPPORT: PVC FOAM  
 SUBSTRATE: PP  
 CERT NO.: 221221 - 1310



**INTEVA MX650011 Type III**

OEM Rev Date: Mar 08

Adhesion Performance Requirements of Pressure Sensitive Adhesive Coated Parts (Minimal Stress) Type III  
 5.3 For a part bonded at a Tier 1 supplier and mechanically fastened on line adhesion:

Passing Type III Meets and Exceeds Type I and II Requirements

**TAPE REQUIREMENTS:**

**4. REQUIREMENTS**

**SECTION 4.3.1 Creep Resistance**

4.3.1, A Initial, Bonded @ 25°C, 50% RH - 7 Days @ 40°C

Specification  
**No Lifting or Shifting**

Results  
 Stable, No Lifting or Removal

Status  
**Pass**

**SECTION 4.3.2 Peel Adhesion**

4.3.2, A Bonded @ 25°C, 50% RH - 20 mins @ RT

Specification  
**350 N / m**

Results  
 363.7

Status  
**Pass**

**SECTION 4.3.3 Impact**

4.3.3, A Bonded @ 25°C, 50% RH, - 20 mins @ RT

Specification  
**No Separation from 2 Impacts**

Results  
 No Impact Separation

Status  
**Pass**

**SECTION 4.3.4 Edge Adhesion**


4.3.4, A Bonded @ 25°C, 50% RH - 20 mins @ RT

Specification  
**Securely Bonded**

Results  
 Stable, No Lifting or Removal

Status  
**Pass**

CERTIFIED BY:



Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.