TEST REPORT



250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com URL: tapes.averydennison.com

PRODUCT: FT 8217 SUPPORT: **SCRIM FELT** SUBSTRATE: **ABS**

230105 - 1105 CERT NO.:



Status

Pass

INTEVA MX650011 Type IV-CYCLE-E

OEM Rev Date: Mar 08

Adhesion Performance Requirements of Pressure Sensitive Adhesive Coated Parts (Minimal Stress)

Results

1041.4

Type IV

5.4 For a part bonded on line or at a Tier 1 supplier, with no additional mechanical

fastening, and subjected to low stress during service:

Passing Type IV Meets and Exceeds Type I, II and III Requirements

TAPE	REQUIREMENTS:
------	---------------

SECTION 4.3.2 Peel Adhesion

4.3.2, A Bonded @ 25°C, 50% RH - 20 mins @ RT

4. REQUIREMENTS

SECTION 4.3.1 Creep Resistance	Specification No Lifting or Shifting	<u>Results</u>	Status
4.3.1, A Initial, Bonded @ 25°C, 50% RH - 7 Days @ 40°C		Stable, No Lifting or Removal	Pass

4.3.1, Cycle E Environments No Lifting or Shifting Stable, No Lifting or Removal **Pass**

Specification

350 N/m

4.3.2, Cycle E Environments			
72 hrs @ 70°C	350 N/m	1071.2	Pass
24 hrs @ 38°C / 95% RH	350 N/m	1048.4	Pass
8 hrs @ -30°C	350 N/m	998.8	Pass
40 hrs @ 70°C	350 N/m	1002.9	Pass
24 hrs @ 38°C / 95% RH	350 N/m	953.9	Pass
8 hrs @ -30°C	350 N/m	1036.2	Pass

SECTION 4.3.3 Impact	Specification	Results	<u>Status</u>
4.3.3, A Bonded @ 25°C, 50% RH, - 20 mins @ RT	No Separation from 2 Impacts	No Impact Separation	Pass

4.3.3, Cycle E Enviro

ironments			
72 hrs @ 70°C	No Separation from 2 Impacts	No Impact Separation	Pass
24 hrs @ 38°C / 95% RH	No Separation from 2 Impacts	No Impact Separation	Pass
8 hrs @ -30°C	No Separation from 2 Impacts	No Impact Separation	Pass
40 hrs @ 70°C	No Separation from 2 Impacts	No Impact Separation	Pass
24 hrs @ 38°C / 95% RH	No Separation from 2 Impacts	No Impact Separation	Pass
8 hrs @ -30°C	No Separation from 2 Impacts	No Impact Separation	Pass

SECTION 4.3.4 Edge Adhesion	Specification	Results	Status
4.3.4, A Bonded @ 25°C, 50% RH - 20 mins @ RT	Securely Bonded	Stable, No Lifting or Removal	Pass

4 3 4 Cycle F Environments	Securely Ronded	Stable No Lifting or Removal	Page

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

ISSUE DATE:

1-1-24

1-16-2018