



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FT 0900X**  
 SUPPORT: **FLOCK**  
 SUBSTRATE: **ABS**  
 CERT NO.: **231128 - 1341**

**ASTM D1000**  
 OEM Rev Date: 41274



**TAPE REQUIREMENTS:**

SECTION : **Peel Adhesion - ABS**  
 Initial, 20 mins @ RT

ASTM D1000

Specification  
**4 N / cm**

Results  
 15.2

Status  
**Pass**

High Temp, 7 days @ 82°C

**11.6 N / cm**

15.7

**Pass**

Cycles (5X)

4 hrs @ 70°C  
 4 hrs @ 38°C / 95-100% RH  
 16 hrs @ -29C

**11.6 N / cm**

15.0

**Pass**

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.