



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 8392 12 PT BD**
 SUPPORT: **PEU FOAM**
 SUBSTRATE: **PP**
 CERT NO.: **230103 - 0827**



CHRYSLER MS-AY-301-B1
 OEM Rev Date : Apr 03
 Cellular Polyurethane - Low Density
 Cellular Polyurethane with Room Temp PSA
 Type 1 - Table 2

TEST PARAMETERS:

Requirements for a Room Temp PSA

SECTION: 3.3.2 Adhesion Test	ASTM D903	<u>Specification</u>	<u>Results</u>	<u>Status</u>
2.1, Adhesion Test, Initial, Room Temp		274 N / m	1294.8	Pass

SECTION: 3.3.2 Adhesion Test	ASTM D903	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Adhesion Test, 2.2, Heat Aged, 168 hrs @ 60°C		330 N / m	2063.6	Pass

SECTION: 3.3.2 Adhesion Test		<u>Specification</u>	<u>Results</u>	<u>Status</u>
2.3, Adhesion Test, After Thermo-Cycling Cycles, 2x Table 2 70°C 24 hrs @ 70°C 24 hrs @ 38°C / 95% RH 24 hrs @ -30°C Repeat twice then 168 hrs @ 70°C		No Loss of Adhesion or Detrimental Effect	Good, Stable No Lifting	Pass

SECTION: 3.3.2 Adhesion Test		<u>Specification</u>	<u>Results</u>	<u>Status</u>
2.4, Adhesion Test, Heat Resistance, 8 hrs @ 70°C		No Shrinkage, Loss of Adhesion or Detrimental Effect	Good, No Adhesion Loss or Lift	Pass

CERTIFIED BY: 
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.