



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8327
SUPPORT: EPDM FOAM
SUBSTRATE: TPE
CERT NO.: 221222 - 0832

CHRYSLER MS-AY-430 C1
OEM Rev Date: May 11
Die-Cut Ethylene Propylene Diene Monomer (EPDM) Closed Cell Rubber
Type 1
C - Cellular EPDM with PSA and Polyester Film

TEST PARAMETERS:

SECTION: 5.0 Adhesion

Specification: No Adhesion Loss or Separation
Adhesion, Environment Cycling, Cycles (2X)
72 hrs @ 70° C
24 hrs @ 38° C / 95% RH
72 hrs @ -40° C

Results Status
Good, Stable, no Lifting Pass

SECTION: 5.0 Adhesion Test

Specification: 274
Adhesion Test, 20 mins @ RT

ASTM D903
N / m

Results Status
446.6 Pass

CERTIFIED BY:

[Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.