| | TEST REPORT | | |
|------------------------------------|----------------------|-----------------------|--|
| | PRODUCT: SUPPORT: | FT 8397 SHODDY PAD | |
| 250 Chester Street | SUBSTRATE: | ABS | |
| Painesville, Ohio 44077 | CERT NO .: | 230103 - 0830 | |
| Phone: 866-GO-AVERY (866-462-8379) | | | |

Fax:

email:

URL:

888-358-4469

TAPE REQUIREMENTS:

psa.tape@averydennison.com

tapes.averydennison.com



CHRYSLER MS-AY-518-B1 OEM Rev Date: Oct 10

Ethylene Vinyl Acetate (EVA) - Cellular - Water and Dust Seals

| Table 2 Physical Properties of Adhesive SysteTEST:1.Initial1, Initial, 20 mins @ Room Temp | ASTM D903-98 10 | Specification 274 N / m | <u>Results</u> 405.7 | <u>Status</u> Pass |
|--|--------------------|---|--|-----------------------------|
| TEST: 2. Extended Term Heat Aging 2, Extended Term Heat Aging *, 168 hrs @ 70°C | * ASTM D573 -08 * | Specification 330 N / m | <u>Results</u> 333.9 | <u>Status</u> Pass |
| TEST: 3. Thermo Cycling 4.3.1 3, Thermo Cycling 4.3.1 - Grade 2 High Temp 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C 24 hrs @ -29°C 2 Cycles then 168 hrs @ 79°C 168 hrs @ 79°C | | Specification No Shrink, Loss of Adhesion or Detrimental Effect | <u>Results</u> No Lifting, Shrink or Loss of Adhesion | <u>Status</u> Pass |
| TEST: 4. Short Term Heat Aging 4, Short Term Heat Aging *, 8 hrs @ 79°C | ASTM D573 -08 * | Specification No Shrink, Loss of Adhesion or Detrimental Effect | <u>Results</u> No Lifting, Shrink or Loss of Adhesion | <u>Status</u> Pass |
| TEST: 8. Burn Rate 8, Initial, Component | FMVSS 302 09 | Specification 100 mm / min | <u>Results</u> Not on Part Model | <u>Status</u> Not Tested |
| | | ISSU | JE DATE: <u>1-1-25</u> | |
| - | produced except in | | he Avery Dennison Performance Tapes. | est. |

This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date:

Page 1 of 1