		TEST REPORT		
		PRODUCT: SUPPORT:	FT 8397 SHODDY PAD	
250 Che	ster Street	SUBSTRATE:	ABS	
Painesvil	lle, Ohio 44077	CERT NO .:	230103 - 0831	
Phone:	866-GO-AVERY (866-462-8379)			
Fax:	888-358-4469	CHRYSLER MS-AY-518-B2		
email:	psa.tape@averydennison.com	OEM Rev Date: Oct 10		



Ethylene Vinyl Acetate (EVA) - Cellular - Water and Dust Seals

TAPE REQUIREMENTS:Table 2 Physical Properties of Adhesive STEST:1.Initial1.Initial1.Initial	Systems	Specification	<u>Results</u>	<u>Status</u>
	ASTM D903-98 10	274 N / m	405.7	Pass
TEST: <b>2. Extended Term Heat Ag</b>		Specification	<u>Results</u>	<u>Status</u>
2, Extended Term Heat Aging *, 168 hrs @ 70°		330 N / m	333.9	Pass
TEST: 3. Thermo Cycling 4.3.1   3, Thermo Cycling 4.3.1 - Grade 2 High Temp 24 hrs @ 79°C   24 hrs @ 38°C / 95% RH 24 hrs @ -29°C   24 hrs @ -29°C 2 Cycles then   168 hrs @ 79°C		Specification No Shrink, Loss of Adhesion or Detrimental Effect	<u>Results</u> No Lifting, Shrink or Loss of Adhesion	<u>Status</u> Pass
TEST: <b>4. Short Term Heat Aging</b> 4, Short Term Heat Aging *, 8 hrs @ 79°C	ASTM D573 -08 *	Specification No Shrink, Loss of Adhesion or Detrimental Effect	<u>Results</u> No Lifting, Shrink or Loss of Adhesion	<u>Status</u> Pass
TEST: <b>8. Burn Rate</b>	FMVSS 302 09	Specification	<u>Results</u>	<u>Status</u>
8, Initial, Component		100 mm / min	Not on Part Model	Not Tested
$\sim$	1 10 1			

CERTIFIED BY:

URL:

tapes.averydennison.com

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 5-7-2010 Page 1 of 1