



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 1158
SUPPORT: EPDM FOAM
SUBSTRATE: PP
CERT NO.: 230105 - 1158



CHRYSLER MS-AY-522 B TYPE 1
OEM Rev Date: Jul 06
Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material
Cellular PVN with PSA

TEST PARAMETERS:

Table with 4 columns: SECTION, Specification, Substrate, Results, Status. Contains three rows for Heat Aging tests (2.1) on ABS and E-COATED METAL substrates.

Table with 4 columns: SECTION, Specification, Substrate, Results, Status. Contains three rows for Adhesion tests (2.2) on ABS and E-COATED METAL substrates.

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.