

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT

FT 8302 PRODUCT: SUPPORT: **PET FOAM**

SUBSTRATE: SS

CERT NO.: 230103 - 0841





Status

CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material

Cellular PVN with PSA

TEST PARAMETERS:

SECTION: 2.1 **Heat Aging** Shrink ASTM D3575-08*

> Specification: < 5% **Substrate Results Status** 2.1, Heat Aging, 30 mins @ 100° C **ABS** Stable, Less than 5% Length and Width **Pass**

Specification: < 5% **Substrate** Results

2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width PP **Pass**

Specification: < 5% **Substrate** Results Status 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width E-COATED METAL **Pass**

Specification: **Substrate Results Status** Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C SS **Pass**

SECTION: 2.2 Adhesion

> Specification: **No Adhesion Loss or Delamiantion**

2.2, Adhesion, Cycles (2X) **Substrate** Results **Status** Good, Stable, no Lifting 72 hrs @ 70° C ABS **Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: **No Adhesion Loss or Delamiantion**

2.2, Adhesion, Cycles (2X) **Substrate Results** Status 72 hrs @ 70° C Good, Stable, no Lifting **Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: **No Adhesion Loss or Delamiantion**

2.2, Adhesion, Cycles (2X) Substrate Results Status 72 hrs @ 70° C Good, Stable, no Lifting E-COATED METAL **Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, , Cycles (2X) Results Substrate Status 72 hrs @ 70° C Good, Stable, no Lifting **Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

CERTIFIED BY:

1-1-25 ISSUE DATE:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

5-1-2005