

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com **TEST REPORT**

PRODUCT: FT B EZ SUPPORT: **PET FOAM**

SUBSTRATE: PP

CERT NO .: 230103 - 0848



CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material

Cellular PVN with PSA

TEST PARAMETERS:

SECTION: 2.1 **Heat Aging** Shrink ASTM D3575-08*

Specification: **Substrate** Results Status 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width **Pass**

<u>Status</u> Specification: < 5% **Substrate Results**

Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C **Pass**

Substrate Specification: < 5% Results **Status** E-COATED METAL Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C **Pass**

Specification: **Substrate** Results < 5% **Status** 2.1, Heat Aging, 30 mins @ 100° C SS Stable, Less than 5% Length and Width **Pass**

SECTION: 2.2 Adhesion

> Specification: No Adhesion Loss or Delamiantion

Results 2.2, Adhesion, Cycles (2X) Substrate Status Good, Stable, no Lifting 72 hrs @ 70° C ABS **Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) **Substrate** Results Status 72 hrs @ 70° C Good, Stable, no Lifting **Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: **No Adhesion Loss or Delamiantion**

2.2, Adhesion, Cycles (2X) **Substrate** Results **Status** Good, Stable, no Lifting **E-COATED METAL** 72 hrs @ 70° C **Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Cycles (2X) Substrate Results **Status** 72 hrs @ 70° C Good, Stable, no Lifting **Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

CERTIFIED BY:

1 - 1 - 25ISSUE DATE:

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Original Test Date:

Page 1 of 1