

**TEST REPORT** 

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

PRODUCT: FT B EZ SUPPORT: **PET FOAM** SUBSTRATE: SS

CERT NO .: 230103 - 0848

**CHRYSLER MS-AY-522 B TYPE 1** 

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material

Cellular PVN with PSA

**TEST PARAMETERS:** 

SECTION: 2.1 **Heat Aging** 

Specification:

2.1, Heat Aging, 30 mins @ 100° C

Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C

Specification: < 5%

2.1, Heat Aging, 30 mins @ 100° C

Specification: < 5%

2.1, Heat Aging, 30 mins @ 100° C

Shrink ASTM D3575-08\*

**Substrate** 

Stable, Less than 5% Length and Width

**Substrate** 

Substrate

E-COATED METAL

**Substrate** 

SS

Substrate

ABS

**Substrate** 

**Substrate** 

**E-COATED METAL** 

Substrate

**Results** Stable, Less than 5% Length and Width

Results

Stable, Less than 5% Length and Width

Results

Good, Stable, no Lifting

Original Test Date:

Results

Results

**Status** Stable, Less than 5% Length and Width **Pass** 

ANSI National Accreditation Board

ACCREDITED

**TESTING LABORATORY** 

Status

**Pass** 

**Status** 

**Pass** 

**Status** 

**Pass** 

Status

**Pass** 

Status

**Pass** 

**Status** 

**Pass** 

**Status** 

**Pass** 

SECTION: 2.2 Adhesion

> Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: **No Adhesion Loss or Delamiantion** 

2.2, Adhesion, Cycles (2X)

72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

No Adhesion Loss or Delamiantion

2.2, Cycles (2X)

Specification:

72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

1 - 1 - 25ISSUE DATE:

Page 1 of 1

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.