

250 Chester Street

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

Painesville, Ohio 44077

email: psa.tape@averydennison.com

URL: tapes.averydennison.com **TEST REPORT** 

PRODUCT: FT B SUPPORT: **PET FOAM** 

SUBSTRATE: SS

CERT NO .: 230103 - 0848 ANSI National Accreditation Board ACCREDITED

**TESTING LABORATORY** 

**CHRYSLER MS-AY-522 B TYPE 1** 

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material

Cellular PVN with PSA

**TEST PARAMETERS:** 

SECTION: 2.1 **Heat Aging** 

Specification:

2.1, Heat Aging, 30 mins @ 100° C

Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C

Specification: < 5%

2.1, Heat Aging, 30 mins @ 100° C

Specification: < 5%

2.1, Heat Aging, 30 mins @ 100° C

Shrink ASTM D3575-08\*

**Substrate** 

**Substrate** 

Stable, Less than 5% Length and Width

Substrate

E-COATED METAL

**Substrate** SS

Substrate

ABS

**Substrate** 

**Substrate** 

**E-COATED METAL** 

Substrate

Results

Results

Stable, Less than 5% Length and Width

**Results** 

Results

Stable, Less than 5% Length and Width

Results

Good, Stable, no Lifting

Original Test Date:

Stable, Less than 5% Length and Width

**Status Pass** 

Status

**Pass** 

<u>Status</u>

**Pass** 

**Status** 

**Pass** 

Status

**Pass** 

Status

**Pass** 

**Status** 

**Pass** 

**Status** 

**Pass** 

SECTION: 2.2 Adhesion

> Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification:

No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification:

**No Adhesion Loss or Delamiantion** 

2.2, Adhesion, Cycles (2X)

72 hrs @ 70° C 24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification:

No Adhesion Loss or Delamiantion

2.2, Cycles (2X)

72 hrs @ 70° C 24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

CERTIFIED BY:

Dave Nichols Jr. Automotive Lab Technician

1 - 1 - 25ISSUE DATE:

Page 1 of 1

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.