



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FBR 1950**
 SUPPORT: **NITRILE VINYL FOAM**
 SUBSTRATE: **ABS**
 CERT NO.: **230103 - 0842**



CHRYSLER MS-AY-545 B1
 OEM Rev Date: Oct 10
 Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation
 B1 - with Room Temp PSA

TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resistance	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3, Heat Resistance, Type 1 Adhesive Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass

SECTION: 3.0 Heat Resistance	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3, Heat Resistance, Type 2 Adhesive Cycles (2X) 72 hrs @ 79° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass

SECTION: 3.4 Adhesion Test	ASTM D903-98	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.4, Adhesion Test, 20 mins @ RT		0.9 N / cm	5.5	Pass

SECTION: 3.6 Flammability	FMVSS 302	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6, Flammability, Initial, As Component		100 mm / minute	< B 25	Pass

CERTIFIED BY:

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.