



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: stus.averydennison.com

PRODUCT: FT 8327
SUPPORT: PET FOAM
SUBSTRATE: PP
STD CERT NO.: 230103 - 0939

CHRYSLER MS-AY-545 C1
OEM Rev Date: Feb 06
Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation
C1 - with Room Temp PSA and backing

TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resistance
3, Heat Resistance, Type 1 Adhesive
Cycles (2X)
72 hrs @ 70° C
24 hrs @ 38° C / 95% RH
72 hrs @ -40° C
Specification: No Adhesion Loss or Delamination
Results: Good, Stable, No Lifting
Status: Pass

SECTION: 3.0 Heat Resistance
3, Heat Resistance, Type 2 Adhesive
Cycles (2X)
72 hrs @ 79° C
24 hrs @ 38° C / 95% RH
72 hrs @ -40° C
Specification: No Adhesion Loss or Delamination
Results: Good, Stable, No Lifting
Status: Pass

SECTION: 3.4 Adhesion Test
3.4, Adhesion Test, 20 mins @ RT
ASTM D903-98
Specification: 0.9 N / cm
Results: 11.5
Status: Pass

SECTION: 3.6 Flammability
3.6, Flammability, Initial, As Component
FMVSS 302
Specification: 100 mm / minute
Results: EBRZT
Status: Pass

CERTIFIED BY:

[Signature]

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.