



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FBA 1960 12 PT BD**
SUPPORT: **EPDM FOAM**
SUBSTRATE: **PP**
CERT NO.: **230103 - 0946**



CHRYSLER MS-AY-545 C2
OEM Rev Date: Oct 10
Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation
C2 - with High Temp PSA and backing


TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resistance	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3, Heat Resistance, Type 1 Adhesive Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass

SECTION: 3.0 Heat Resistance	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3, Heat Resistance, Type 2 Adhesive Cycles (2X) 72 hrs @ 79° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass

SECTION: 3.4 Adhesion Test	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.4, Adhesion Test, 20 mins @ RT ASTM D903-98 10	0.9 N / cm	5.2	Pass

SECTION: 3.6 Flammability	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6, Flammability, Initial, As Component FMVSS 302 09	100 mm / minute	< B 25	Pass

CERTIFIED BY: 
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.