

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

888-358-4469 Fax:

psa.tape@averydennison.com email: URL:

tapes.averydennison.com

## **TEST REPORT**

PRODUCT: FM 2455 SUPPORT: 2 MIL FOIL SUBSTRATE: **GLASS** 

230103 - 0948 CERT NO .:



OFM Rev Date: Oct 10

Adhesion - PSA, Low Density Foam Sealing Applications

B - Supported Adhesive for Die Cut Parts



TAPE REQUIREMENTS:

SECTION: 2.2 (A) Adhesion **Specification Results Status** 2.2 (A), Adhesion, 24 hrs @ RT No Adhesion Loss or Lifting Good, Stable, No Lifting **Pass** 

SECTION: 2.2 (B) Adhesion Specification Results **Status** No Adhesion Loss or Lifting Good, Stable, No Lifting 2.2 (A), Adhesion, 250 hrs @ 79°C **Pass** 

SECTION: 2.2 (C) Adhesion Specification Results **Status** 

No Adhesion Loss or Lifting Good, Stable, No Lifting 2.2 (A), Adhesion, 250 hrs @ 38°C / 100% RH **Pass** 

SECTION: 2.2 (D) Adhesion **Specification Results Status** 

Good, Stable, No Lifting 2.2 (A), Adhesion, Cycles (3x) No Adhesion Loss or Lifting **Pass** 72 hrs @ 79°C

24 hrs @ 38°C / 95% RH

72 hrs @ -40°C

**Specification** SECTION: 3.0 (A) Results Status 4.4 N/cm 3.0 (A), , 24 hrs @ RT 17.6 **Pass** 

**Specification** SECTION: 3.0 (B) **Results Status** 3.0 (A), , 250 hrs @ 79°C 4.4 N/cm 18.6 **Pass** 

SECTION: 3.0 (C) **Specification Results Status** 

3.0 (A), , 250 hrs @ 38°C / 100% RH 4.4 N/cm 10.2 **Pass** 

SECTION: 3.0 (D) **Specification** Results **Status** 3.0 (A), Cycles (3x) 4.4 N/cm 9.7 **Pass** 

72 hrs @ 79°C

24 hrs @ 38°C / 95% RH

72 hrs @ -40°C

CERTIFIED BY: ISSUE DATE: 1-1-25

Dave Nichols Jr. Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.