

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

psa.tape@averydennison.com email:

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126 SUPPORT: **CARPET**

SUBSTRATE: PP

CERT NO.: 230103 - 0948

CHRYSLER MS-CC255 OEM Rev Date: Oct 04

Adhesion - PSA, Low Density Foam Sealing Applications

B - Supported Adhesive for Die Cut Parts

ACCREDITED TESTING LABORATORY

TAPE REQUIREMENTS:

SECTION: 3.0 (A) Adhesion 3.0 (A), Adhesion, 24 hrs @ RT CLP 463TB-3-01A*

Specification No Adhesion Loss or Lifting

Results Good, Stable, No Lifting Status **Pass**

SECTION: 3.0 (A) Adhesion 3.0 (A), Adhesion, 250 hrs @ 79°C

CLP 463TB-10-01*

Specification No Adhesion Loss or Lifting

Results Good, Stable, No Lifting Status **Pass**

ASTM D1735

Results

Status

SECTION: 3.0 (A) Adhesion 3.0 (A), Adhesion, 250 hrs @ 38°C / 100% RH

CLP 463CB-10-01*

Specification No Adhesion Loss or Lifting

Specification

No Adhesion Loss or Lifting

Good, Stable, No Lifting

Results

Good, Stable, No Lifting

Pass

Status

Pass

SECTION: 3.0 (A) Adhesion

3.0 (A), Adhesion, Cycles (3x)

24 hrs @ 79°C 24 hrs @ 38° C / 95% RH

24 hrs @ -29°C

SECTION: 4.0 180 Degree Peel | CLP 463TB-3-01A*

4.0 (A), 180 Degree Peel Test, 24 hrs @ RT

Specification 0.45 N/mm

Results 8.0

Status Pass

SECTION: 4.0

180 Degree Peel | CLP 463TB-10-01*

4.0 (A), 180 Degree Peel Test, 250 hrs @ 79°C

Specification 0.3 N/mm

Results 0.7

1.0

Results

0.6

Status Pass

Status

Pass

SECTION: 4.0

180 Degree Peel | ASTM D1735 4.0 (A), 180 Degree Peel Test, 250 hrs @ 38°C /

Specification 0.9 N/mm

Specification

0.27 N/mm

Results **Status Pass**

SECTION: 4.0

180 Degree Peel TestCLP 463CB-10-01*

4.0 (A), 180 Degree Peel Test, Cycles (3x)

Cycles (3x) 24 hrs @ 79°C

24 hrs @ 38° C / 95% RH

24 hrs @ -29°C

ISSUE DATE:

1-1-25

CERTIFIED BY:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.