

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

888-358-4469 Fax:

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126 SUPPORT: **UHMWPE** SUBSTRATE: **ABS**

CERT NO .: 230103 - 0949

CHRYSLER MS-CH-612 OEM Rev Date: Oct 04

Adhesive Rquirements, Pressure Sensitive Adhesive

Low Friction



TEST PARAMETERS:

CLP 463TB-4-01* **Specification** SECTION: 6.3 **Tensile Strength** 35 N / cm 6.3, Tensile Strength, A. Initial @ RT

53.1

Peel Adhesion SECTION: 6.3

6.3, Peel Adhesion, B. Initial @ RT

CLP 463TB-3-01* **Specification** 3.5 N/cm

Results 13.2

Results

Status Pass

Status

Pass

SECTION: 6.3 **Peel Adhesion**

6.3, Peel Adhesion, B. 168 hrs @ 79° C

CLP 463CB-10-01* **Specification**

3.5 N/cm

Results 7.2

Status Pass

SECTION: 6.3 **Peel Adhesion**

6.3, Peel Adhesion, B. 168 hrs @ 38° C / 95% RH

ASTM 1735

Specification 3.5 N/cm

Results 17.5

Status **Pass**

SECTION: 6.3 **Peel Adhesion**

6.3, Peel Adhesion, B. Cycles (2X)

24 hrs @ 79° C

24 hrs @ 38° C / 95% RH

24 hrs @ -29° C

Specification 3.5 N/cm

Results 6.0

Status Pass

SECTION: 6.3 **Shear Adhesion** 6.3, Shear Adhesion, C. Initial @ RT

CLP 463TB-8-01*

CLP 463CB-10-01*

Specification 104 kPa

Results 267.3

Status Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Original Test Date:

10-5-2009

Page 1 of 1