



## TEST REPORT

250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

PRODUCT: FT 1150  
SUPPORT: 5 MIL BLUE UHMWPE  
SUBSTRATE: ABS  
CERT NO.: 230103 - 0949



CHRYSLER MS-CH-612  
OEM Rev Date: Oct 04  
Adhesive Requirements, Pressure Sensitive Adhesive  
Low Friction

### TEST PARAMETERS:

SECTION: 6.3 Tensile Strength 6.3, Tensile Strength, A. Initial @ RT	CLP 463TB-4-01*	<u>Specification</u> 35 N / cm	<u>Results</u> 73.2	<u>Status</u> Pass
SECTION: 6.3 Peel Adhesion 6.3, Peel Adhesion, B. Initial @ RT	CLP 463TB-3-01*	<u>Specification</u> 3.5 N / cm	<u>Results</u> 4.8	<u>Status</u> Pass
SECTION: 6.3 Peel Adhesion 6.3, Peel Adhesion, B. 168 hrs @ 79° C	CLP 463CB-10-01*	<u>Specification</u> 3.5 N / cm	<u>Results</u> 11.2	<u>Status</u> Pass
SECTION: 6.3 Peel Adhesion 6.3, Peel Adhesion, B. 168 hrs @ 38° C / 95% RH	ASTM D1735	<u>Specification</u> 3.5 N / cm	<u>Results</u> 11.3	<u>Status</u> Pass
SECTION: 6.3 Peel Adhesion 6.3, Peel Adhesion, B. Cycles (2X) 24 hrs @ 79° C 24 hrs @ 38° C / 95% RH 24 hrs @ -29° C	CLP 463CB-10-01*	<u>Specification</u> 3.5 N / cm	<u>Results</u> 8.1	<u>Status</u> Pass
SECTION: 6.3 Shear Adhesion 6.3, Shear Adhesion, C. Initial @ RT	CLP 463TB-8-01*	<u>Specification</u> 104 kPa	<u>Results</u> 187.7	<u>Status</u> Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.