

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

888-358-4469 Fax:

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

## **TEST REPORT**

PRODUCT: FT 1150 SUPPORT: **UHMWPE** SUBSTRATE: **ABS** 

CERT NO .: 230103 - 0949

CHRYSLER MS-CH-612 OEM Rev Date: Oct 04

Adhesive Rquirements, Pressure Sensitive Adhesive

Low Friction



**TEST PARAMETERS:** 

CLP 463TB-4-01\* **Specification** Results SECTION: 6.3 **Tensile Strength Status** 35 N / cm 53.6 **Pass** 6.3, Tensile Strength, A. Initial @ RT

**Peel Adhesion** SECTION: 6.3 CLP 463TB-3-01\* **Specification Results Status** 7.8 **Pass** 

6.3, Peel Adhesion, B. Initial @ RT 3.5 N/cm

CLP 463CB-10-01\* **Specification** SECTION: 6.3 **Peel Adhesion Results Status** 3.5 N/cm 7.1 6.3, Peel Adhesion, B. 168 hrs @ 79° C **Pass** 

SECTION: 6.3 **Peel Adhesion ASTM 1735 Specification** Results Status

6.3, Peel Adhesion, B. 168 hrs @ 38° C / 95% RH 3.5 N/cm 7.7 **Pass** 

SECTION: 6.3 **Peel Adhesion** CLP 463CB-10-01\* **Specification Results Status** 3.5 N/cm 5.4 **Pass** 

6.3, Peel Adhesion, B. Cycles (2X)

24 hrs @ 79° C

24 hrs @ 38° C / 95% RH

24 hrs @ -29° C

CLP 463TB-8-01\* **Specification** Results SECTION: 6.3 **Shear Adhesion Status Pass** 

6.3, Shear Adhesion, C. Initial @ RT 104 kPa 261.4

**CERTIFIED BY:** 

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.