



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: 866-GO-AVERY (866-462-8379)  
 Fax: 888-358-4469  
 email: psa.tape@averydennison.com  
 URL: tapes.averydennison.com

**TEST REPORT**

PRODUCT: FT 1150  
 SUPPORT: UHMWPE  
 SUBSTRATE: SS  
 CERT NO.: 230103 - 0949



**CHRYSLER MS-CH-612**  
 OEM Rev Date: Oct 04  
 Adhesive Rquirements, Pressure Sensitive Adhesive  
 Low Friction

**TEST PARAMETERS:**

SECTION:	Test Description	Reference	Specification	Results	Status
6.3	Shear Adhesion 6.3, Shear Adhesion, A. Initial @ RT	CLP 463TB-4-01*	35 N / cm	66.2	Pass
6.3	Shear Adhesion 6.3, Shear Adhesion, B. Initial @ RT	CLP 463TB-3-01*	3.5 N / cm	5.7	Pass
6.3	Shear Adhesion 6.3, Shear Adhesion, B. 168 hrs @ 79° C	CLP 463CB-10-01*	3.5 N / cm	11.6	Pass
6.3	Shear Adhesion 6.3, Shear Adhesion, B. 168 hrs @ 38° C / 95% RH	ASTM D1735	3.5 N / cm	10.3	Pass
6.3	Shear Adhesion 6.3, Shear Adhesion, B. Cycles (2X) 24 hrs @ 79° C 24 hrs @ 38° C / 95% RH 24 hrs @ -29° C	CLP 463CB-10-01*	3.5 N / cm	11.5	Pass
6.3	Shear Adhesion 6.3, Shear Adhesion, C. Initial @ RT	CLP 463TB-8-01*	104 kPa	159.4	Pass

CERTIFIED BY:   
 Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.  
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.  
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.