|--|--|

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TEST REPORT

FT 8392

NYLON

PEU FOAM

230103 - 1011

PRODUCT: SUPPORT: SUBSTRATE: CERT NO.: ANSI National Accreditation Board A C C R E D I T E D ISO/IECITO25 TESTING LABORATORY

DELPHI SD2-324 OEM Rev Date: May 08 Pressure Sensitive Adhesives for HVAC Sealing Applications Classification Requirements 4.3 Permanent Bond Adhesive

TAPE REQUIREMENTS:SECTION: 3.3Service Temperature3.3.1, Permanent Bond, 96 hrs @ -40°C	Specification No Adhesion Loss or Separat	ion Good, Stable, No Lifting Pass	
3.3.1, High Temp Permanent Bond, 96 hrs @ 121°C	No Adhesion Loss or Separat	ion Good, Stable, No Lifting Pass	s
SECTION: 3.4 Humidity 3.4, Humidity, 50 hrs @ 38°C / 95% RH	Specification No Adhesion Loss, Discoloration or Soft	<u>Results</u> <u>Statu</u> ening Stable, No Lifting or Visible Change Pass	
SECTION: 3.5 Objectionable Odor 3.5, Service Temperature, 1 hr @ 93°C	Specification 2 or Less Rating	ResultsStatu2Pass	
3.5, Service Temperature, 1 hr @ 93°C, 1 hr @ RT	2 or Less Rating	2 Pass	S
SECTION: 3.6 Fogging, Oil Bath 3.6, 6 hrs @ 85°C, 21°C Cooling, 16 hrs @ RT	GM 9305P 92 Specification 60 Units	ResultsStatu97.7Pass	
SECTION: 3.7 Creep 3.7, Creep, Ambient, 3.5 hrs @ 23°C	Specification No Slip	ResultsStatuNo SlipPass	_
SECTION: 4.3 Peel Test 4.3.1.1 (A), Peel Test, As Bonded @ RT	GMW 14124 10 600 N / m	702.2 Pass	s
4.3.1.1 (B), Peel Test, 72 hrs @ 93°C	350 N / m	1291.1 Pass	s
4.3.1.1 (C), Peel Test, 24 hrs @ -40°C	350 N/m	888.9 Pass	S
4.3.1.1 (D), Peel Test, 48 hrs @ 38°C / 100% RH	350 N/m	1130.0 Pass	S
4.3.1.1 (E), Peel Test, 800 hrs @ 93°C	350 N / m	544.6 Pass	S
SECTION: 4.3 Static Shear 4.3.1.2, Static Shear, Ambient, 3.5 hrs @ 23°C	No Slip	ResultsStatuNo SlipPass	
SECTION: 4.3 Tensile Elongation 4.3.1.3, Static Shear, Tensile, PET Only	ASTM D882-10 1750 N / m	ResultsStatu2801.6Pass	
4.3.1.3, Static Shear, Elongation, PET Only	60 %	121.7 Pass	s

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 9-15-2004 Page 1 of 1