



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8299
SUPPORT: 2MIL PET
SUBSTRATE: SS
CERT NO.: 221222 - 0838

FCA MS-AY-350 S Type 2
OEM Rev Date: Oct 16
Cellular Polyester Polyurethane Foam - Low Density
Cellular Polyurethane with High Temp PSA
Table 1: Mechanical and Physical Property Requirements

TAPE REQUIREMENTS:

SECTION: 3 Low Temperature Flexibility
Low Temperature Flexibility, 180° Bend - 24 hrs @ -40°C
Specification: No Cracking
Results: Stable, No Cracks or Breaking
Status: Pass

SECTION: 4 Adhesion After Environment Cycles
Adhesion After Environment Cycles, Cycles (2x)
72 hrs @ 79°C
24 hrs @ 38°C / 98% RH
24 hrs @ -40°C
Specification: No Delamination
Results: No Adhesion Loss or Lifting
Status: Pass

SECTION: 5 Odor
Odor, Dry, 1 hr @ 79°C
SAE J1351
Specification: 3 Max
Results: 2 - Slight, But Noticeable Odor
Status: Pass

Odor, Wet, 1 hr @ 79°C - Deionized Water
3 Max
2 - Slight, But Noticeable Odor
Pass

Signature of Dave Nichols Jr.
Dave Nichols Jr, Automotive Lab Technician

CERTIFIED BY:

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.