

250 Chester Street Painesville. Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 1115

SUPPORT: TAN NONWOVEN

SUBSTRATE: ABS

230103 - 0950 CERT NO .:

FCA MS-CB-134

OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid

ACCREDITED

TESTING LABORATORY

substrate with the application of pressure.

**TEST PARAMETERS:** 

**Specification** SECTION: 3.2 **Adhesive Peel Strength** Results **Status** 2.7 N/cm 8.9 Initial, 24 hrs @ RT **Pass** 

Results SECTION: 3.2 **Adhesive Peel Strength** LP-463CB-10-01 **Specification** Status 1.8 N/cm 9.4 **Pass** 168 hrs @ 79°C

**Adhesive Peel Strength** SECTION: 3.2 **Specification Status** ASTM D17363CB-10-01 **Results** 168 hrs @ 38°C / 98% RH 2.2 N/cm 15.3 **Pass** 

SECTION: 3,2 **Specification Adhesive Peel Strength Results** LP-463CB-10-01 **Status** 2.2 N/cm 10.2 **Pass** 

Cycles, 3X

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

SECTION: 3.3 **Shear Adhesion Specification** Results **Status** Initial, 24 hrs @ RT 55 kPa 182.7 **Pass** 

SECTION: 3.3 **Shear Adhesion** I P-463CB-10-01 **Specification** Results Status

198.1 168 hrs @ 79°C 48 kPa **Pass** 

SECTION: 3.3 **Shear Adhesion ASTM D1735 Specification** Status Results 122.0 168 hrs @ 38°C / 98% RH 55 kPa **Pass** 

SECTION: 3,3 **Shear Adhesion** LP-463CB-10-01 **Specification** Results Status 55 kPa 103.8 **Pass** 

Cycles, 3X

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

ISSUE DATE: **CERTIFIED BY:** 1-1-25

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.