TEST REPORT



250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

PRODUCT: FT 1126
SUPPORT: LEATHER
SUBSTRATE: ABS

CERT NO.: 230103 - 0951



Page 1 of 1

FCA MS-CB-134

OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid

substrate with the application of pressure.

TEST PARAMETERS:

SECTION: 3.2 Initial, 24 hrs @ F	Adhesive Peel Strength		Specification 2.7 N / cm	<u>Results</u> 11.5	Status Pass
SECTION: 3.2 168 hrs @ 79°C	Adhesive Peel Strength	LP-463CB-10-01	Specification 1.8 N/cm	Results 12.3	Status Pass
SECTION: 3.2 168 hrs @ 38°C /	Adhesive Peel Strength 98% RH	ASTM D17063CB-10-01	Specification 2.2 N / cm	Results 13.0	Status Pass
24 hrs	Adhesive Peel Strength s @ 79°C s @ 38°C / 95% RH s @ -29°C	LP-463CB-10-01	Specification 2.2 N/cm	<u>Results</u> 11.6	<u>Status</u> Pass

SECTION: 3.3 Shear Adhesion Initial, 24 hrs @ RT			Specification	<u>Results</u>	Status
			55 kPa	355.2	Pass
SECTION: 3.3 168 hrs @ 79°C	Shear Adhesion	LP-463CB-10-01	Specification 48 kPa	Results 351.2	Status Pass

SECTION: 3.3	Shear Adhesion	ASTM D1735	Specification	<u>Results</u>	<u>Status</u>
168 hrs @ 38°C / 98% RH			55 kPa	288.4	Pass

SECTION: 3.3	Shear Adhesion	LP-463CB-10-01	Specification	<u>Results</u>	<u>Status</u>
Cycles, 3X			55 kPa	299.6	Pass

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

CERTIFIED BY: ISSUE DATE: 1-1-25

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.