

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TEST	REPORT
-------------	--------

PRODUCT:	FT 1126
SUPPORT:	LEATHER
SUBSTRATE:	FIBER BOARD
CERT NO .:	230103 - 0951



FCA MS-CB-134

OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid substrate with the application of pressure.

TEST PARAMETERS:SECTION: 3.2Adhesive Peel StrengthInitial, 24 hrs @ RT		Specification 2.7 N / cm	<u>Results</u> 6.7	<u>Status</u> Pass
SECTION: 3.2 Adhesive Peel Strength 168 hrs @ 79°C	LP-463CB-10-01	Specification 1.8 N / cm	Results 12.0	<u>Status</u> Pass
SECTION: 3.2 Adhesive Peel Strength	ASTM D17:63CB-10-01	Specification	<u>Results</u>	<u>Status</u>
168 hrs @ 38°C / 98% RH		2.2 N / cm	13.5	Pass
SECTION: 3.2 Adhesive Peel Strength Cycles, 3X 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C	LP-463CB-10-01	Specification 2.2 N / cm	<u>Results</u> 12.8	<u>Status</u> Pass
SECTION: 3.3 Shear Adhesion		Specification	<u>Results</u>	<u>Status</u>
Initial, 24 hrs @ RT		55 kPa	245.9	Pass
SECTION: 3.3 Shear Adhesion	LP-463CB-10-01	Specification	Results	<u>Status</u>
168 hrs @ 79°C		48 kPa	333.9	Pass
SECTION: 3.3 Shear Adhesion	ASTM D1735	Specification	<u>Results</u>	<u>Status</u>
168 hrs @ 38°C / 98% RH		55 kPa	245.9	Pass
SECTION: 3.3 Shear Adhesion Cycles, 3X 24 hrs @ 79°C	LP-463CB-10-01	Specification 55 kPa	Results 266.4	<u>Status</u> Pass

24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C

ISSUE DATE:

1-1-25

Dave Nichols Jr, Automotive Lab Techniclan

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 6-26-2017

Page 1 of 1