



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1149X
SUPPORT: GRAY VINYL
SUBSTRATE: ABS
CERT NO.: 230103 - 0952



FCA MS-CB-134

OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System
Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid substrate with the application of pressure.

TEST PARAMETERS:

SECTION:	Test Name	Spec	Specification	Results	Status
3.2	Adhesive Peel Strength Initial, 24 hrs @ RT		2.7 N / cm	18.0	Pass
3.2	Adhesive Peel Strength 168 hrs @ 79°C	LP-463CB-10-01	1.8 N / cm	7.0	Pass
3.2	Adhesive Peel Strength 168 hrs @ 38°C / 98% RH	ASTM D17363CB-10-01	2.2 N / cm	14.1	Pass
3.2	Adhesive Peel Strength Cycles, 3X 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C	LP-463CB-10-01	2.2 N / cm	3.8	Pass
3.3	Shear Adhesion Initial, 24 hrs @ RT		55 kPa	186.6	Pass
3.3	Shear Adhesion 168 hrs @ 79°C	LP-463CB-10-01	48 kPa	470.7	Pass
3.3	Shear Adhesion 168 hrs @ 38°C / 98% RH	ASTM D1735	55 kPa	200.8	Pass
3.3	Shear Adhesion Cycles, 3X 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C	LP-463CB-10-01	55 kPa	345.8	Pass

CERTIFIED BY:
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.