

250 Chester Street Painesville. Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1149X

SUPPORT: TAN NONWOVEN

SUBSTRATE: ABS

230103 - 0953 CERT NO .:



OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid

ACCREDITED

TESTING LABORATORY

Pass

3.7

substrate with the application of pressure.

TEST PARAMETERS:

SECTION: 3.2 **Specification Adhesive Peel Strength** Results **Status** 2.7 N/cm 7.1 Initial, 24 hrs @ RT **Pass** SECTION: 3.2 **Adhesive Peel Strength** LP-463CB-10-01 **Specification** Results Status

168 hrs @ 79°C

1.8 N/cm

Adhesive Peel Strength SECTION: 3.2 **Specification** Results **Status** ASTM D17363CB-10-01 168 hrs @ 38°C / 98% RH 2.2 N/cm 6.2 **Pass**

SECTION: 3,2 **Specification Adhesive Peel Strength Results** LP-463CB-10-01 **Status** Cycles, 3X 2.2 N/cm 3.7 **Pass**

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

SECTION: 3.3 **Shear Adhesion Specification** Results **Status** Initial, 24 hrs @ RT 55 kPa 110.6 **Pass**

SECTION: 3.3 **Shear Adhesion** I P-463CB-10-01 **Specification** Results Status 100.8 168 hrs @ 79°C 48 kPa **Pass**

SECTION: 3.3 **Shear Adhesion ASTM D1735 Specification** Status Results 127.1 168 hrs @ 38°C / 98% RH 55 kPa **Pass**

SECTION: 3,3 **Shear Adhesion** LP-463CB-10-01 **Specification** Results Status 55 kPa 90.7 **Pass** Cycles, 3X

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

ISSUE DATE: **CERTIFIED BY:** 1-1-25

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.