



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126 12 PT BD
SUPPORT: FLOCK
SUBSTRATE: PP
CERT NO.: 230103 - 1035



FCA MS-JZ-8-22
OEM Rev Date: Dec 16
Anti-Squeak Fabric, Pressure Sensitive

TAPE REQUIREMENTS:

SECTION:	ASTM D3884	Specification	Results	Status
Wear Resistance				
Taber Abrasion, Dry, 1000 Cycles, CS-10, 1000 g Load		No Noticeable Wear or Adhesive / Fiber Loosening	No Loosening of Fibers or Adhesive	Pass
Taber Abrasion, Wet, 1000 Cycles, CS-10, 500 g Load		No Noticeable Wear or Adhesive / Fiber Loosening	No Loosening of Fibers or Adhesive	Pass
Odor	SAE J1351	Specification	Results	Status
Dry, 1 hr @ 79°C		No Disagreeable Odor	2 - Slight, But Noticeable Odor	Pass
Wet, 1 hr @ 79°C - Deionized Water		No Disagreeable Odor	1 - No Noticeable Odor	Pass
Flammability	FMVSS 302	Specification	Results	Status
Initial, Component		< 101.6 mm / min	< B 85	Pass
Tape Tests	LP-463LB-19-01	Specification	Results	Status
A. Original, 20 mins @ RT, Tape Tests,		No Adhesive Lifting	Good, Stable, No Lifting	Pass
B. 168 hours @ 110°C, Tape Tests,		No Adhesive Lifting	Good, Stable, No Lifting	Pass
C. Cycles (2X), Tape Tests, 16 hrs @ 38°C / 95% RH 24 hrs @ 110°C 6 hrs @ -29°C		No Adhesive Lifting	Good, Stable, No Lifting	Pass
D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Tape Tests,		No Adhesive Lifting	Good, Stable, No Lifting	Pass
Bond Peel Tests	ASTM D1000	Specification	Results	Status
A. Original, 20 mins @ RT, Bond Peel Tests,		5.5 N / cm	8.4	Pass
B. 168 hours @ 110°C, Bond Peel Tests,		4 N / cm	6.4	Pass
C. Cycles (2X), Bond Peel Tests, 16 hrs @ 38°C / 95% RH 24 hrs @ 110°C 6 hrs @ -29°C		3.5 N / cm	9.4	Pass
D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Bond Peel Te		3.5 N / cm	11.5	Pass
Resistance to Non-Condensing Humidity	LP-463KB-12-01	Specification	Results	Status
Resistance to Non-Condensing Humidity <i>As Reported by Supplier</i>		No fade, color changes or loosening of fibers	Not Tested	Not Tested
Resistance to Crocking Wet / Dry	SAE J861	Specification	Results	Status
Resistance to Crocking Wet <i>As Reported by Supplier</i>		4 Min Rating	Not Tested	Not Tested
Resistance to Crocking Dry		4 Min Rating	Not Tested	Not Tested

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.