

**TEST REPORT**



250 Chester Street  
Painesville, Ohio 44077  
Phone: **866-GO-AVERY (866-462-8379)**  
Fax: **888-358-4469**  
email: **psa.tape@averydennison.com**  
URL: **tapes.averydennison.com**

PRODUCT: **FT A902**  
SUPPORT: **FLOCK**  
SUBSTRATE: **ABS**  
CERT NO.: **231017 - 0816**

**FCA MS-JZ-8-22**  
OEM Rev Date: Dec 16  
**Anti-Squeak Fabric, Pressure Sensitive**



**TAPE REQUIREMENTS:**

SECTION:	ASTM	Specification	Results	Status
<b>Wear Resistance</b> Taber Abrasion, Dry, 1000 Cycles, CS-10, 1000 g Load	ASTM D3884	<b>No Noticeable Wear or Adhesive / Fiber Loosening</b>	Worn But Not Thru	<b>Pass</b>
Taber Abrasion, Wet, 1000 Cycles, CS-10, 500 g Load		<b>No Noticeable Wear or Adhesive / Fiber Loosening</b>	Worn But Not Thru	<b>Pass</b>
<b>Odor</b> Dry, 1 hr @ 79°C	ASTM J1351	<b>No Disagreeable Odor</b>	11 - Not Tested	<b>Not Tested</b>
Wet, 1 hr @ 79°C - Deionized Water		<b>No Disagreeable Odor</b>	11 - Not Tested	<b>Not Tested</b>
<b>Flammability</b> Initial, Component	FMVSS 302	<b>&lt; 101.6 mm / min</b>	< B 75	<b>Pass</b>
<b>Tape Tests</b> A. Original, 20 mins @ RT, Tape Tests,	LP-463LB-19-01	<b>No Adhesive Lifting</b>	Good, Stable, No Lifting	<b>Pass</b>
B. 168 hours @ 110°C, Tape Tests,		<b>No Adhesive Lifting</b>	Good, Stable, No lifting	<b>Pass</b>
C. Cycles (2X), Tape Tests, 16 hrs @ 38°C / 95% RH 24 hrs @ 110°C 6 hrs @ -29°C		<b>No Adhesive Lifting</b>	Good, Stable, No lifting	<b>Pass</b>
D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Tape Tests, 24		<b>No Adhesive Lifting</b>	Good, Stable, No lifting	<b>Pass</b>
<b>Bond Peel Tests</b> A. Original, 20 mins @ RT, Bond Peel Tests,	ASTM D1000	<b>7 N / cm</b>	9.8	<b>Pass</b>
B. 168 hours @ 110°C, Bond Peel Tests,		<b>8 N / cm</b>	8.3	<b>Pass</b>
C. Cycles (2X), Bond Peel Tests, 16 hrs @ 38°C / 95% RH 24 hrs @ 110°C 6 hrs @ -29°C		<b>9.5 N / cm</b>	9.6	<b>Pass</b>
D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Bond Peel Test:		<b>9 N / cm</b>	12.4	<b>Pass</b>
<b>Resistance to Non-Condensing Humidity</b> Resistance to Non-Condensing Humidity <i>As Reported by Supplier</i>	LP-463KB-12-01	<b>No Fade, Color Changes or Loosening of Fibers</b>	Not Tested	<b>Not Tested</b>
<b>Resistance to Crocking Wet / Dry</b> Resistance to Crocking Wet <i>As Reported by Supplier</i>	SAE J861	<b>4 Min Rating</b>	Not Tested	<b>Not Tested</b>
Resistance to Crocking Dry		<b>4 Min Rating</b>	Not Tested	<b>Not Tested</b>

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.