



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 333**
SUPPORT: **LYTHERM**
SUBSTRATE: **ABS**
CERT NO.: **230103 - 1153**



FCA PF-10770
OEM Rev Date: Feb 15
Adhesion - PSA, Cellular and Fibrous Materials
Table 2 Flexible Composites

*** FCA 2015 Revision Requirements Are for Steel, Plastic Requirements to be Determined*

TAPE REQUIREMENTS:

| SECTION: | Heat Resistance | LP-463TB-03-01* | Specification | Results | Status |
|----------|---|-----------------|------------------------------------|----------------------------------|-------------|
| 2.2, | Heat Resistance, Initial, 2 hrs @ RT | | No Adhesion Loss or Lifting | Stable, No Lift or Adhesion Loss | Pass |
| SECTION: | Heat Resistance | LP-463CB-10-01* | Specification | Results | Status |
| 2.2, | Heat Resistance, 168 hrs @ 79°C | | No Adhesion Loss or Lifting | Stable, No Lift or Adhesion Loss | Pass |
| SECTION: | Heat Resistance | LP-463CB-10-01* | Specification | Results | Status |
| 2.2, | Heat Resistance, 8 hrs @ 93°C | | No Adhesion Loss or Lifting | Stable, No Lift or Adhesion Loss | Pass |
| SECTION: | Heat Resistance | | Specification | Results | Status |
| 2.2, | Heat Resistance, 24 hrs Water Immersion | | No Adhesion Loss or Lifting | Stable, No Lift or Adhesion Loss | Pass |
| SECTION: | Heat Resistance | ASTM D1735 | Specification | Results | Status |
| 2.2, | Heat Resistance, Cycles (5x) 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C | | No Adhesion Loss or Lifting | Stable, No Lift or Adhesion Loss | Pass |
| SECTION: | Peel Adhesion | LP-463TB-03-01* | Specification | Results | Status |
| 3.0, | Adhesion, Initial, 2 hrs @ RT | | 0.9 N / cm | 2.4 | Pass |
| SECTION: | Peel Adhesion | LP-463CB-10-01* | Specification | Results | Status |
| 3.0, | Adhesion, 168 hrs @ 79°C | | 3.3 N / cm | 8.3 | Pass |
| SECTION: | Peel Adhesion | LP-463CB-10-01* | Specification | Results | Status |
| 3.0, | Adhesion, 8 hrs @ 93°C | | 3.3 N / cm | 10.4 | Pass |
| SECTION: | Peel Adhesion | | Specification | Results | Status |
| 3.0, | Adhesion, 24 hr Water Immersion | | 3.3 N / cm | 4.0 | Pass |
| SECTION: | Peel Adhesion | ASTM D1735 | Specification | Results | Status |
| 3.0, | Adhesion, Heat Resistance, Cycles (5x) 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C | | 3.3 N / cm | 9.6 | Pass |

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.