

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

psa.tape@averydennison.com email:

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8217

NITRILE VINYL FOAM SUPPORT:

SUBSTRATE: TALC PP CERT NO .: 230103 - 1210

FCA PF-10770

OEM Rev Date: Feb 15

Adhesion - PSA. Cellular and Fibrous Materials

Table 2 Flexible Composites



TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resistance LP-463TB-03-01*

2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: 3.0 Heat Resistance LP-463CB-10-01*

2.2, Heat Resistance, 168 hrs @ 79°C

Heat Resistance LP-463CB-10-01* SECTION: 3.0

2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: 3.0 **Heat Resistance**

2.2, Heat Resistance, 24 hrs Water Immersion

2.2, Heat Resistance, Cycles (5x)

SECTION: 3.0

SECTION: 3.0

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

Heat Resistance ASTM D1735

24 hrs @ -29°C

Specification

No Adhesion Loss or Lifting

Specification

0.9 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

SECTION: 3.0 **Peel Adhesion**

3.0, Adhesion, Initial, 2 hrs @ RT

LP-463CB-10-01* **Peel Adhesion**

LP-463TB-03-01*

3.0, Adhesion, 168 hrs @ 79°C

SECTION: 3.0 **Peel Adhesion** LP-463CB-10-01*

3.0, Adhesion, 8 hrs @ 93°C

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, 24 hr Water Immersion

SECTION: 3.0 **Peel Adhesion ASTM D1735**

3.0, Adhesion, Heat Resistance, Cycles (5x)

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

ACCREDITED

TESTING LABORATORY

Pass

Status

Pass

Status

Pass

Status

Status

Pass

Status

Pass

Results Status 3.3 **Pass**

Results

Status Pass

3.8

8.5

Results Status

Pass

Results

Status **Pass**

4.9

Status

Results 3.3

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.