

250 Chester Street Painesville, Ohio 44077 Phone: 866-GO-AVERY (866-462-8379) Fax: 888-358-4469 psa.tape@averydennison.com email: URL: tapes.averydennison.com

TAPE REQUIREMENTS:

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, 168 hrs @ 79°C

Heat Resistance SECTION: 3.0 2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C

SECTION: 3.0	Peel Adhesion
3.0, Adhesion,	Initial, 2 hrs @ RT

SEC 3.0,

SEC 3.0.

SEC 3.0,

SEC 3.0, Adhesion, Heat Resistance, Cycles (5x) Adhesion, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH

TEST REPORT

PRODUCT: SUPPORT: SUBSTRATE: CERT NO .:

FT 0900X FLOCK E-COATED METAL 230103 - 1059

FCA PF.90175

OEM Rev Date: Mar 15 Pressure Sensitive Adhesives Includes Chrysler Standard PF-10770 Table 2 Flexible Composites

Specification

Specification

No Adhesion Loss or Lifting

Specification

No Adhesion Loss or Lifting

Specification

No Adhesion Loss or Lifting

Specification

No Adhesion Loss or Lifting

No Adhesion Loss or Lifting



Results	<u>Status</u>
Good, Stable, No Staining or Removal	Pass
Results	Status

Pass

Results Stable, No Lift or Adhesion Loss

Results Status Stable, No Lift or Adhesion Loss Pass

Results <u>Status</u> Stable, No Lift or Adhesion Loss Pass

Results Status Stable, No Lift or Adhesion Loss Pass

CTION: 3.0 Peel Adhesion	Specification	<u>Results</u>	<u>Status</u>
), Adhesion, Initial, 2 hrs @ RT	0.9 N / cm	5.5	Pass
CTION: 3.0 Peel Adhesion 250 Chester Street	Specification	<u>Results</u>	<u>Status</u>
), Adhesion, 168 hrs @ 79°C	3.3 N / cm	14.0	Pass
CTION: 3.0 Peel Adhesion 250 Chester Street	Specification	<u>Results</u>	<u>Status</u>
), Adhesion, 8 hrs @ 93°C	3.3 N / cm	14.6	Pass
CTION: 3.0 Peel Adhesion	Specification	Results	<u>Status</u>
), Adhesion, 24 hr Water Immersion	3.3 N / cm	4.6	Pass
CTION: 3.0 Peel Adhesion	Specification	<u>Results</u>	<u>Status</u>
), Adhesion, Heat Resistance, Cycles (5x)	3.3 N / cm	14.7	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

7-11-2017

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: